



HYDROTINT HPX RANGE – HIGH PERFORMANCE

DVM Pigments & Additives

Innovative Colour. Enviably Quality.

The Hydrotint HPX range of aqueous pigment dispersions has been specifically formulated to give the following properties:

- Very High Light and Weather Fastness
- High Tinting Strength
- Bright Colours
- Flocculation Resistance
- Alkylphenol Ethoxylate Free
- Compatibility with a Wide Range of Coatings
- Good Storage Stability

HYDROTINT HPX-RANGE – PRODUCT DATA

Product	Pigment Type	Pigment Content (%)	Light Fastness		Weather Fastness*		Acid Resistance	Alkali Resistance
			Mid Shade	Pale Shade	Mid Shade	Pale Shade		
Hydrotint Yellow HP 3GX	C.I. Pigment Yellow 93	37	8	8	5	5	5	5
Hydrotint Yellow HP 4GX	C.I. Pigment Yellow 151	44	8	8	5	5	5	5
Hydrotint Yellow Oxide YX FDA	C.I. Pigment Yellow 42	55	8	8	5	5	5	5
Hydrotint Orange HP RX	C.I. Pigment Orange 36	40	7-8	6-7	5	4-5	5	5
Hydrotint Red Oxide MX FDA	C.I. Pigment Red 101	57	8	8	5	5	5	5
Hydrotint Red HP S2RX	C.I. Pigment Red 254	38	8	8	5	5	5	5
Hydrotint Magenta EX	C.I. Pigment Red 122	35	7-8	7	5	5	5	5
Hydroflex Violet 19 FDA (Blue Shade)	C.I. Pigment Violet 19	37	7	7	4-5	3-4	5	5
Hydroflex Violet QXR FDA (Red Shade)	C.I. Pigment Violet 19	37	7	7	4-5	3-4	5	5

PRODUCT DATA (CONTINUED)

Product	Pigment Type	Pigment Content (%)	Light Fastness		Weather Fastness*		Acid Resistance	Alkali Resistance
			Mid Shade	Pale Shade	Mid Shade	Pale Shade		
Hydroflex Violet 23 V2	C.I. Pigment Violet 23	30	7	7	5	4	5	5
Hydrotint Blue AX	C.I. Pigment Blue 15:0	47	8	7-8	5	4-5	5	5
Hydrotint Blue GX	C.I. Pigment Blue 15:3	47	8	7-8	5	4-5	5	5
Hydrotint Green GX	C.I. Pigment Green 7	50	8	8	5	5	5	5
Hydroflex Green 6GS FDA	C.I. Pigment Green 36	46	8	7-8	5	4-5	5	5
Hydrotint Black BXT3	C.I. Pigment Black 7	45	8	8	5	5	5	5

*2000 hours weatherometer

Light Fastness - Determined from coatings exposed to light in a Xenon Arc test chamber
The Light Fastness rating is assessed using the fade of Blue Wool Standards. 1= Poor, 3= Fair, 8= Excellent.

Weather Fastness - The amount of shade change seen in coatings that are exposed for 12 months exterior weathering.
Shade changes are assessed by using a 1-5 Grey Scale. 1 indicates severe change, 5 indicates no change.

CONTACT US:

Primrose Mill, Ratcliffe Street, Darwen, Lancashire, BB3 2BZ

Tel: +44 (0)1257 278995 | Fax: +44 (0)1257 270491

Email: sales@dvpigments.co.uk | dvpigments.co.uk

USE THIS QR CODE TO
DOWNLOAD THE LATEST
PRODUCT BROCHURES.



ABOUT DVM PIGMENTS & ADDITIVES

DVM Pigments & Additives (DVM) is a supplier of quality products to the surface coatings industry. As a joint investment arm of TRCC and Excelkos Group of Malaysia, DVM is supported by more than 100 years of combined latex, dispersion and emulsion experience.



DVM Pigments & Additives

For more information about our company, visit dvpigments.co.uk.

NOTE: The data given us based on the present state of our knowledge and experience. We would recommend doing your own tests and assessment prior to purchase. The represented colour shades are given as a guide only. As an ISO 9001:2015 company our procedures and quality management are second to none.